

Sustainable Flexible Composite : An Upcoming Development in Technical Textile

S. Basak*, D.B. Shakyawar, Kartick K Samanta, Niranjana Kumar, S. Ghosh

ICAR-National Institute of Natural Fibre Engineering and Technology, 12 Regent Park, Kolkata: 700040

Abstract

The current review context elaborates on the engineering methods adopted by the researchers for the development of different sustainable flexible composites for use as an alternative to leather like material. This article also elaborates on the usage of different natural fibre-based cellulose, bacterial cellulose, and different plant-based compounds for the construction of leather like lifestyle products with the examination report of essential physical properties of engineered products. Besides, it elucidates the process conditions followed by the researchers for making natural fibre based flexible composite products

Keywords:

Plant based flexible composite, leather, natural fibre, Cellulose

Citation

S. Basak, D.B. Shakyawar, Kartick K Samanta, Niranjana Kumar, S. Ghosh - "Sustainable Flexible Composite: An Upcoming Development in Technical Textile", *BTRA Scan* - Vol. LII No. 3, July 2023, Page no. 10 to 17

1.0 Introduction

Generally, natural leather production and processing involved a larger quantity of toxic synthetic chemicals like sulphuric acid, sodium hydroxide, formaldehyde, heavy metal salt, chrome treatment etc. These chemicals have increased the biological oxygen demand (BOD), Chemical Oxygen demand (COD), and Total dissolved solids (TDS) level of effluent water and polluted the surrounding environment with different harmful microbes and foul chemical-based smell. In addition, the slaughtering of animals for the raw source of leather hide is another major concern. Therefore, the development of artificial leather is getting attention from industries and researchers. Artificial leather made from the elastomeric coating (mainly polyvinyl chloride, polyurethane etc.) of synthetic fibres is also popular in different trade names into the commercial market. Major advantages of the products are high impact resistance, light weight, flexibility, high abrasion resistance, tensile strength and cheaper cost [1, 2,3,4]. However, these products are not eco-friendly and could affect the user's feet due to microbes, and fungus generation, and could generate bad odour on continuous usage due to lack of breathability and water vapor permeability [5-7]. Apart from these mentioned difficulties, now a day, the world is moving towards sustainability and as per the Animal Rights Act, the collection of leather from animal origin is also almost banned in some of the countries. Therefore, researchers and entrepreneurs are searching for suitable sustainable alternatives to leather for human beings. In this direction,

natural fibre based footwear is an attractive and appropriate addition. Natural fibres from the cellulosic background are having high modulus, tensile strength and a moderately high coefficient of friction, abrasion resistance, lightweight, breathability and aristocratic eco-friendly look [8-10]. In addition, fibres from the protein background like wool are soft, thermally non-conductive and flexible and also can transmit water vapor easily into the surroundings [11-13]. In the last decade, different commercial companies are marketed natural fibre based footwear products. Different kinds of elastomeric coating (PVC, polyurethane, nitrile rubber, sterile butadiene rubber, acrylonitrile butadiene rubber, neoprene etc.) on the natural fibre is also popular in the market. However, it is also not completely eco-friendly due to the long synthetic chain of rubber present in the coated composite material. Therefore, natural rubber is slowly getting popularity as a coated material on the natural fibre and also has been used as the sole material of footwear. In this direction, natural fibre also has been used by researchers as a reinforcing agent with rubber as the sole material of footwear [14-17]. Incorporation of the natural fibre in the rubber-based formulation has increased its toughness, tensile strength, coefficient of friction etc. In addition of it, Functionality in terms of antimicrobial (insole), anti-odour (insole), water and dust repellent (outer shell), and moisture management properties (lining material) are very important for the end users and few research works also have been accomplished on the outer textile material and also on the composite layer of the outer shell of footwear [18-22]. To the best of our knowledge, to date, no comprehensive review is

*Corresponding author,

E-mail: shantanubasak@gmail.com

there on the exploration of natural fibre for the engineering of footwear products and the creation of artificial leathers.

In the current context, a comprehensive review is represented on the exploration of natural fibre for making footwear materials with their important physical properties. In addition, it also systematically represents the usage and performances of rubber coated natural fibre material as the upper part, lining and sole of footwear products. Besides detailed standardized testing parameters are represented with critical discussion on the research lacuna and futuristic approaches in the domain of natural fibre based footwear materials.

1.1 Natural leather processing

Natural leather could be processed by the following technical sequence. Detail processing methods are discussing in below section [23-25]

- a. Curing- Raw hides from different part of the country has come in the leather industries. Raw hides or skins must be preserved by salts or freezing, or chilling to prevent bacterial or microbe attacks [23].
- b. Soaking- The main objective of this step is to rehydrate the hide, as well as to remove any excess salt or dirt from the hide.
- c. Liming- This process assists to remove hair from hides. Alkali (Lime- $\text{Ca}(\text{OH})_2$) and sodium sulphide both are used for this purpose. This is more commonly referred to as a "pelt".
- d. Fleshing- This process involves passing the pelt through a machine that removes fatty layers of the flesh side of the pelt. Pelt will also be split into layers at this stage.
- e. Deliming- This step involves lowering of alkaline pH of processed leather and turning it to acidity. Normally it is done by ammonium chloride and other organic salt.
- f. Bating- This process is applied to flatten or relax the pelt by the use of enzymes.
- g. Pickling- Bated pelt come into the most important pickling section of the leather industry. Tanning requires pelts to be mildly acidic whereas pickling involves the application of acid and salt solution. If a pelt is not to be tanned for several months a strong solution may be applied to act as a preservative. Therefore for storage purposes of untanned leather, pickling is a necessary step.
- h. De- Greasing- For tanning purposes, a pelt should be free from excess grease. It is performed by water or a mild solvent [24-25].
- i. Tanning- A variety of types of tanning follow in leather industries, but the most common is chrome tanning or vegetable tanning. After chrome tanning, leather hide becomes blue and it is called "wet blue" leather in the commercial market. Vegetable tanning plant extracts may be used to produce thick, firm, and brown leather, ideal for belts, shoes, bags, and cases. This process is mainly used for the preparation of gloves or soft items.
- j. Splitting- In this step, a machine is used to slice leather into two layers. One of the resulting layers will be without a grain surface. This piece can be used to produce suede or have an artificial grain surface applied to it.
- k. Shaving- The grain surface stays with that piece, another machine is used to shave the non grain side. This is how leather is made to a desired level of this thickness.
- l. Neutralization- This step in how leather is made is done to remove residuals from any of the previous chemical applications. Additional tanning materials may also be applied to create a particular style or texture in the finished product [24,25].
- m. Dyeing- Depending upon the intended use of the finished leather, any number of colours may be applied at this stage. This is how leather is made in black, red, brown and even white varieties [25].
- n. Fatliquoring- This process involves lubricating the leather with oil to ensure that it is both flexible and soft. This is especially important when producing leather for fashion etc.
- o. Samming- Moisture must be taken out of the leather before it will be ready for production. Almost half of the water is removed through several different machines [24,25].
- p. Setting out- The leather is now stretched and the grain surface is smoothed out. In so doing, the moisture remaining in the leather is further reduced.
- q. Final drying- Leather is generally dried until less than 20% water content remains.
- r. Staking & Dry Drumming- To ensure that the leather is soft and flexible, it is further massaged in a staking machine. This process separates the fibres. Once complete, the leather is placed inside a rotating drum for extensive tumbling.
- s. Buffing & Brushing- The flesh surface of the leather is now totally removed through buffing to produce a softer feel, or simply to reduce the overall thickness. A thorough brushing happens thereafter to remove any dust accumulated during buffing.
- t. Finishing- Finishing occurs in leather production to ensure even colour, remove any defects on the grain

surface, correct the level of gloss, and add a protective and water-resistant surface.

- u. Final-Grading- Grading of the leather was performed depending on feel, softness, thickness, and texture.

1.2 Variation of the process for different types of leather material

All leather items depend on the process of manufacture (tanning process). In the gloves materials (soft material) most important factor is the usage of fat liquor chemical in a high percentage, but hard materials (bags, belts) are mainly manufactured from vegetable-tanned leather. "Nappa" leather is very soft and flexible, used normally in the car seat cover and as a furniture covering material [26-28]. Different kind of lifestyle leather articles depends on the process and percentage of chemicals. Extra polish and roller effect need to soft and flappy articles and also final coating/dyeing mechanical operation apply depending on the final products. In mechanical processes like the staking process, open fibres of leather are by stacked machine and resulted in softy materials [29]. Most often chemicals and mechanical operations lead to different to many kinds of leather products.

From the aforementioned part, it was quite clear that leather processing requires a huge quantity of water, chemicals, heavy metal salts etc. Especially It may cause harmful effects on the effluent as well as on the surrounding atmosphere. However, natural leather has huge demand in the commercial market for its long-term use, physical strength, flex resistance, enriched tensile properties etc.

2. Plant-based flexible composite

2.1 Plant-based and natural fibre based flexible composite products

Recently, "vegan" terminology is very much popular in the world market because it nullifies the usage of any animal-based product or by-product for using leather materials. Although there are many official issues with the usage of this terminology. Usually "vegan leather" made from plant and vegetable background are also getting popularity because of its sustainability, lower animal harm, breathability and more bio-degradability. Snap-pap is vegan leather, recently available in the market. It looks like a paper material and it is a mixture of cellulose and latex. It is available in different colours like light brown, dark brown, black etc [30]. Teak leaf leather is another example of sustainable leaf-based vegan leather. As per the literature it is made of Teak leaves, cotton non-woven fabric and a thin lamination of natural chemicals on the outside of the leaf. Thin lamination made the material waterproof, lightweight and high tear resist product [31]. Two layered cotton non-woven bind with acrylic-based binders has been placed on the back side of the

leaves and the upside of the leaf was coated with a thin polyolefin layer. This leather also could be made from the leaves of some other plants like bananas, pineapple, kambucha leaves etc [32]. The physical properties of snap-pap leather have been represented in Table 1.. Velarde et al 2019 reported the use of cactus leaf for making cactus leather due to its rugged thick skin. It is a fantastic bio-mimicking approach and they have reported that initially cactus leaf has been cleaned and mashed. Thereafter it has been sundried for a particular period before dyeing with natural reagents [33]. Cactus leathers are used for producing car seats, shoes, bags and wallets from cactus leather. One London-based commercial branch has launched a leather based product from mango. They have wastage mangoes available in the commercial market. They have also revealed the technology of mashing and boiling the mangoes. However, in detail, technology has not been revealed by the researcher in the open platform [34]. Apart from it, recently, other vegan leathers from grapes, mushrooms etc., also have been launched in the market. As per reported literature, the roots of mushrooms contain mycelium and continuous dispersion of mycelium on sawdust and agricultural waste created a thick matt of natural leather and its polymeric composition is the same as the composition of the shells of crabs. However, lots of technical problems are there for the commercial viability of the mushroom leather-like product [35]. Recently, Kerelia et al 2020 have prepared bacterial cellulose from coconut water. As per the mentioned process, they have left coconuts in the sterilize water for the culture of bacteria. Jelly-like viscous materials have generated after 12-14 days of impregnation in water and they are mixed with banana fibre or gum and produced a continuous 3D sheet of natural leather like material. Finally, they have air dried and softened the sheet for further usage into different end products like footwear, bags, wallets etc., [36].

Artificial leather from bacterial cellulose, in this line, researchers have further reported that *Acetobacter Xylinum*, a gram-negative soil bacteria has been used for the synthesis of natural cellulose. They synthesized cellulose in the laboratory and compared its properties with natural animal leather [37]. In this direction, another research group have developed cellulose through *Komagataeibacte* (genre) bacteria. These bacteria engulf tea leaves and produce cellulose film. After drying, this material produced soft bovine leather and it is useful for orthopaedic footwear applications because of its soft nature [38]. According to the reported literature, this cellulosic material is very soft and could be used as the sole material for orthopaedic patients. Plant-origin-based vegan leather is quite new, promising and emerging research area in the domain of artificial leather and a lot of research opportunities are there in this direction.

Natural fibre based flexible composite

In 2004, a research patent has been filed on the application of textile based upper material for the engineering of athletic footwear. They have adopted the weft knitting process for making of the textile based upper part of the footwear. The research group claimed that the prepared upper part accepts ventilation and performs a proper cooling effect on the underlying foot on the sole. Prepared sole material has a great cushioning effect and also succeeds to provide traction or control effect during foot movement. As per their claim, they have used three-layer system of knitted structures. Exterior layer has good wear resistance, flexibility and air permeability. Intermediate layer lightweight polymer foam that provides a cushioning effect and protects the foot from objects that may contact the upper. Finally, the interior layer was made of a textile material having good moisture-wicking properties and removing perspiration from the contact area of the foot. They have joined the three layers by adhesive and also by mechanical-based stitching process [2]

Researchers have pointed out some important attributes of natural fibre for its application as footwear material. Properties like heat and moisture transference, absorption, air permeability, tension strength, weight, thickness, shape etc., are important for footwear application. Very recently Nam et al 2019 reported the engineering method of multilayer natural fibre based components as an alternative to leather. They have claimed that the material is completely sustainable. They have used cellulosic fibre mat, denim fabric and hemp fabric and compared its properties with the leather arrangement made with calf and pig leather. As per the report, both the arrangement has same properties in terms of break force and total heat loss [26]. The shoe lining is the material inside the shoe that comes in contact with the entire foot. It is composed of side, upper and heels. A research group has reported the physical and thermal comfort characteristics of the knitted fabrics used for shoe linings [12,15]. They have made spacer fabric by knitting two entirely different fabrics, having different properties and making a unique structure. Cotton and cotton/ bamboo blended yarn was used for making flat and interlock knitted spacer fabric. They have shown that the material shows excellent compression elasticity, cushioning, air permeability and breathability, high thermal insulation and temperature regulation [15]. The cotton/ rayon blend combination showed better frictional resistance whereas the cotton/ bamboo weft knitted structure showed comfort under hot weather conditions [15].

In the year of 2017, one company named Hugo Boss launched pineapple leaf fibre based footwear products in the market. It is marketed as a trade name of "Pinatex". They are claiming that the upper part of the shoe is made of pineapple leaf fibre and is dyed with natural dye [39]. Recently as per the published report, they have launched sneakers and

chappal like products in the commercial market. As per their report, pineapple leaf fibre has been felted into a nonwoven structure and used for making the upper part of the footwear. They have endorsed that the waste of almost 16 pineapple plants has been used for 1 square meter of Pinatex [40]. The prepared footwear is soft, lightweight and also delivers breathability. Reports endorse that Pinatex is inherently shower resistant and dirt materials deposited could be easily wiped by moist cloth. In the mid of the year 2021, one company named Dope Kicks launched hemp fibre based water repellent footwear. They have prepared woven textiles by using strong hemp fibre and added one chemical based coating on the outer surface of the footwear for water resistance and for avoiding dust and dirt on the surface of the footwear. They have reported that the insole of the footwear has been made by using cork, a natural material that can provide antibacterial action and also deliver cushioning effect to the end users [41].

Another part of this context has mainly covered artificial leather containing natural fibre as base material. Natural rubber consists of 2000 isoprene units (C_5H_8) and has low tensile strength, elasticity (viscoelastic), lower resistance to crack initiation and permanent tackiness property (much less than polyester, epoxy, and thermoset resins). Vulcanization of natural rubber forms bridges between the chains of isoprene units and provides strength, elasticity, viscosity, hardness etc. Accelerator-like complex organic compound (stearic acid) has been used in vulcanizing formulation in the presence of activator like zinc oxide. This basic formulation could be used as a coating material on the natural textile surface. In addition of it, the incorporation of a particular amount of filler, cross-linker, and anti-ozone compound is also a challenging issue for rubberized formulation makers. Effective interaction between natural rubber and natural fibre is a major challenging issue. It could be solved by modification of fibre surface or by modification of matrix. Some of the researchers have reported that the graft copolymerization of natural fibre with different monomers like stearic acid, maleic anhydride etc. assists in uniform adhesion, and stress transfer of natural fibre in the rubber matrix. Silane can act as a bridging agent between natural fibre and matrix. Silane is a silicon based chemical that contains hydrophobic groups, almost like an unsaturated hydrocarbon. These groups assist to create functionality on the fibre surface and as a result, it is chemically linked with the rubber matrix and enhanced strength properties. Composite prepared by using silane as bridging material has lowered the scorch time and curing time. Acetylation of fibre surface also could be a good proposition for better fibre and matrix adhesion as it will make the surface of the natural fibre more hydrophobic. Heat treatment (make the surface hydrophobic), and plasma irradiation treatment (assist in functional group generation) of natural fibre also could be explored for making the surface more hydrophobic

[depending on polymerising gas used] and generate adhesion compatibility with natural rubber. Modified matrix like epoxidized natural rubber (more hydrophobic groups) also could be used for improving adhesion property and uniform filler dispersion [42]. These approaches already have been taken by various researchers for making rubber and natural fibre based bio-composite and artificial leather products. It shows that in the presence of a crosslinking agent, natural rubber could be linked with the polar based cellulose background.

3. Mechanism of rubber-cellulose attachment

It is reported that the artificial leather could be engineered by coating natural fibre based canvas cloth with rubber formulation. Thereafter it is coated with cellulose nitrate and has been embossed to get a leather like appearance. In the nineteenth century, Sheesley patented a useful formulation for the coating of natural fibre based textile materials for the engineering of artificial leather. He has engineered multiple wood pulp made sheets into the form of artificial leather by using a mixed formulation of 18-22% rubber solid (latex), 4-7% albumin based gum, 60-65% water, 6-8% ethyl alcohol, ethyl acetate and 1-3% formaldehyde with very minor quantity (1%) of ammonia. Ammonia has been added into the formulation for the stabilization of the latex and formaldehyde removes the odour and assists in the tanning process of the engineered product [43,44]. Jeong et al 2007 proposed a method of preparation of artificial leather by using different compositions of polyester and nylon blend as nonwoven base material having g/m² range from 180-280 and free air volume range 70-90%. They coated the said nonwoven material with polyurethane elastomer by following the wet coagulation method in the coating machine. Air pressure, temperature and humidity level are different from the outer atmosphere, inside the shoe. Therefore, they have measured important physical parameters like air permeability, water vapor permeability, thermal transport etc. for the engineered artificial leather. As per the report, the used nonwoven material showed water vapor permeability of 5000gm/m² day and it has been decreased to 2000gm/m² day after coating. As per the report, heat keeping rate of the nonwoven is decreased after coating with elastomeric material and they have also claimed that the heat flow rate of the coated material has been improved as compared to the nonwoven fabric and as a result, a cool feeling has been observed for the finished product [21]. Wool et al 2013 has patented technology of making artificial leather from natural fibre made fabric and triglyceride based plant oil. They have prepared composite like artificial leather material from nonwoven flax and kenaf fibres and a suitable mixture of soybean oil, linseed oil and thin fatty acid and functionalized monomer (vinyl aromatic or acrylate monomer) [45]. Very recently, one innovative research idea has been reported on the preparation of fully biodegradable

artificial leather by the multi layering approach of natural fibres [23]. The concerned article shows the technical direction for the production of sustainable footwear by using imitation leather made of natural fibre. As per the report, researchers have developed a multilayered cellulosic material based mat by using a tertiary layer of cellulosic mat, denim fabric and hemp fibre made fabric. They have also compared the physical properties of the multi-layered structure with the bilayered calf and pig skins. According to a published report, there is no significant difference between the two structures in terms of breaking force and heat loss. Moreover, the air permeability and water vapor transmission rate of the natural fibre made structure is higher as compared to the real leather [23]. A joint project of NSTEDB and FICCI, in collaboration with IJIRA, has represented that impregnated composite made by jute cotton union fabric could be used as a supplement to natural leather. They have prepared toe puff, counter components, and insole material from it. Toe puff is present in the front part of the shoe in between the leather and lining. They have claimed that the engineered material is more flexible, compact and has high shape retention property as compared to natural leather. They have reported that initially jute cotton union fabric has been treated with the water based polymeric solution for the manufacturing of toe puff and counter stiffener. For further betterment and for meeting international standards, they have treated the water based emulsion treated fabric with hot melt adhesive. However, they have not mentioned the details of the chemicals explored for experimental purposes [12]. In the same year, the concerned scientist filed a patent on the engineering of footwear by using a thermoplastic composite made of jute cotton union fabric and thermoplastic emulsion based formulation. As per their report, they have used styrene monomer with talc, PVA and sterile butadiene rubber for the emulsion based treatment and followed by high temperature curing. They have used formulation based on polystyrene: 25-40%, filler (mineral powder): 10-20%, plasticizer (dioctyl phthalate): 1-3% and solvent (benzene/toluene/acetone) for the preparation of hot melt adhesive required for the engineering of toe puffs. As mentioned in the earlier part, Initially, they treated the jute and jute cotton union fabric with the emulsion and cured the sample. Thereafter they made it into the desired shape of the sole and finished it with the hot melt coating of the adhesive before final use in footwear products [46]. "Noani" is an example of artificial leather based on composite construction. It consists of three layers composed of polyester microfiber material (upper layer), leather fibre board (core layer), and coated textile with foamed PVC and textile carrier (backside layer) [47]. Table 1 shows the comparison of the physical properties of different sustainable leather alternatives in contrast with natural leather.

Table 1 Summary of the Basic structures and important properties of the footwear products made from natural fibre

Natural leather	Important physical properties of natural leather			
	Tensile strength (N/mm ²)	Max elongation (%)	GSM (g/cm ²) & thickness (mm)	Air permeability (cc/s/cm ²)
Natural double layer leather (cow skin and pig skin combination) [8]	14-15	54.9	439 & 2.25	0.006
Natural goat leather [6-7]	12-13	55.61	523 & 1.93	4.6
Synthetic leather	Physical properties of synthetic leather			
Polyester coated with polyurethane [29]	3-4	80-100	550 & 1.4	Less than 1
Sustainable leather alternatives	Important physical properties of leather alternatives			
Cellulosic mat (outer shell), denim fabric and hemp fabric (inner shell) [18,41]	5-7	5-10	641-650 & 2.26	10-15
Jute-cotton mat coated with rubber [45]	4-5	4-5	650 & 2.2	15-20
Linen/flax fibre based leather [35]	12-13	10-14	420-450 & 1.2	10-12
Pineapple fibre based leather [43]	4.5-5.5	15-20	500 & 1.43	8-10
Snap pap leather [30]	3-4	4-5	350-400 & 0.57mm	2-3
Teak leaf leather [31]	2-3	7-10	300-400 & 0.57-1	5-7
Muskin leather [35]	1-1.5	10-15	600-625 & 6-7	10-15
Natural fibre based rubberized flexible composites				
Natural fibre and rubber composite	Important physical properties (Various physical properties)			
Bagasse fibre (30%) +natural rubber [14]	6-7	25-30	Composite hardness: 60shore A	No permeability
Silane modified bamboo fibre+ natural rubber [15] (use in frozen land)	12-13	20-25	700 & 3	Less than 1
5% bleached jute fibre+ natural rubber based formulation [16]	11-12	9-10	600-650 & 4	4-5
Alkali modified pineapple fibre+ natural rubber based formulation [41-43]	5-7	5-10	550-650 & 4-5	1-2

4. Conclusion

The main advantages of natural fibre based flexible composite products are bio-degradable, renewable, soft to skin and also breathable. Comfort and lifetime of the said products are very much important. Different research works are already going on the natural fibre (jute, wool, cotton, pineapple, hemp) based flexible composites. In all cases, natural fibre based woven or non-woven fabric has been used for the engineering of shoe upper part, and lining and for the

preparation of insole and other lifestyle products like wallets, belts, jackets, seat covers etc. However, applications of those products usually are in very limited areas (mainly in-house applications and in dry atmospheres) and the technology is not up to mark as most of them are damaged in moist conditions, easily attacked by microbes, moths (only for woollen footwear) and generate bad odour on continuous usage. In addition of it, the footwear material needs to be more resilient, moldable, lightweight and have adequate

anti-slip (frictional resistance) and impact resistance properties as per the end usage of the concerned product. Moreover, the abrasion resistance property of the natural fibre based footwear (upper part and insole) also needs to be improved by using suitable chemicals or by changing the basic construction parameters of yarn and textile. Some of the natural lignocellulosic fibres like ramie, flax etc., or suitable blends of them could be used for making nonwoven and for engineering upper shoe parts and insole material of footwear products. These ligno-cellulosic fibres have high

ply ability, modulus, bendability, fineness etc. Therefore, the exploration of newer domains of natural fibres could be one important future thrust of this area.

Acknowledgement

We are very much thankful to the Indian Council of Agricultural Research - "Consortia Research Platform of Natural Fibres" for financially sponsoring this project

References

1. Natural coir sole and production method thereof and shoes with soles, 2014, CN104172653A.
2. Article of footwear having textile upper, 2004, US7347011B2
3. <http://www.leather-dictionary.com>, Artificial leather-Imitation leather, leather dictionary
4. <http://www.garrettleather.com>, How do faux leather fabric compare to real leather?
5. Sanchez M, Garotte NC, Maestre I, Bertazzo M (2013), Latest developments in antimicrobial functional materials for footwear in Microbial pathogens and strategies for combating them: science, technology and education, 102-113.
6. Luo Q, Gao H, Peng L, Liu G, Zhang Z (2016) Synthesis of PEGylated chitosan copolymers as efficiently antimicrobial coating for leathers, *Journal of Applied Polymer Science*, 133: 255-275.
7. Udkhiyati M, Rosiati NM, Silvianti F (2020), The influence of chitosan towards antibacterial properties of natural leather, *Leather and Footwear Journal*, 20: 425-434.
8. Meyer M, Dietrich S, Mondschein A, Comparison of technical performance of leather, artificial leather and trendy alternatives, *Coatings*, 2021; 11:226-234.
9. <http://www.bgsuttarakhand.org.in>, Handicraft product, Bhartiya GramotthanSansthan.
10. <http://www.mts-global.com>>upload> Footwear-Booklet- (R1); MTS, Footwear testing guide and requirements
11. <http://www.amexessentials.com>, Pineapple leather: The skin you are (Not) in- Amex essentials.
12. <http://www.materialdistrict.com>, Waterproof hemp shoes- Material District, Retrieved on 2nd July 2019.
13. Insoles made with hemp and manufacturing methods thereof, KR20110024627A, South Korea, 2009.
14. Paiva FFG, Maria VPK, Tores GV, Dognani G, Santos RJ, Sugarcane bagasse fibre as semi-reinforcement filler in natural fibre composite sandals, *Journal of Material Cycles and Waste Management*, 2019, 21, 326-335.
15. Toda T, Okubo K, Fujii T, Hurutachi H, Yamanaka Y, Yamamura H, Development of rubber shoe sole containing bamboo fibres for frozen roads, 16th International Conference on Composite Materials, 2006.
16. Correia CA, Valera TS, Moraes M (2017) The influence of bleached jute fiber filler on the properties of vulcanized natural rubber. *Mater Res* 20:466–471.
17. Kohan L, Martins CR, Duarte LO, Pinheiro L (2019), Panorama of natural fibre applied in Brazilian footwear: Materials and market, *SN Applied Sciences*, 1:895-90
18. Samanta SK, Basak S and Chattopadhyay SK, Environmental friendly denim processing using water free technologies in Sustainability in Denim, Edited by Muthu S, 2017, 319-348, Springer Singapore.
19. Samanta KK, Basak S and Chattopadhyay SK, Eco-friendly coloration and functionalization of textile using plant extracts in Roadmap to sustainable textiles and clothing, Edited by Muthu S, 2014, 263-287, Springer Singapore.
20. Samanta KK, Basak S and Chattopadhyay SK, Environment-friendly processing using plasma and UV treatment in Roadmap to sustainable textiles and clothing, Edited by Muthu S, 2014, 161-201, Springer Singapore.
21. Samanta KK, Basak S and Chattopadhyay SK, Sustainable Flame Retardant Finishing of Textiles in Handbook of sustainable apparel production, Edited by Muthu S, 2015, 45-59, CRC Press, Taylor and Francis group.
22. Samanta KK, Basak S and Chattopadhyay SK, Sustainable dyeing and finishing of textiles using natural ingredients and water-free technologies in Textiles and Clothing Sustainability, Edited by Muthu S, 2017, 99-131, Springer Singapore.
23. Bhavya KS, Selvarani JA, Samrot AV, Thevarkatti LP, Mohamed J, Appalaraju VS, Leather processing, its effect on environment and alternative of chrome tanning, *International Journal of Advance Research and Engineering Technology* 2019; 10: 69-79
24. Maina P, Ollengo MA, Nthiga EW, Trends in leather processing: A review, *International Journal of Science Research*, 2019; 9: 212-223
25. Tharikaivalen P, Rao JR, Nair UB, Ramasami T, Recent trends in the leather making process, problems and pathways, *Critical reviews in Environmental Science and Technology*, 2007; 35: 37-79.

26. Nam C, Lee YA (2019) Multilayered cellulosic material as a leather alternative in the footwear industry, Clothing and Textile Research Journal, 37 (1): 20-34.
27. <http://www.leather-dictionary.com>, Artificial leather-Imitation leather, leather dictionary
28. <http://www.garrettleather.com>, How do faux leather fabric compared to real leather?
29. Jeong WY, Park JW, Kamijo M, Shimizu Y, Kook S, Characteristics of artificial leather for footwear- heat and moisture transport properties, SEN I GAKKAISHI, 63: 271-275.
30. Harne A, Snappap-The new vegan leather, 8th Feb 2018, Weecos Journal, <http://www.sustainablelifestyleblog.com>
31. Joe A, What is leaf leather?-Tree tribe, Retrieved in 29th November 2017, <http://www.treetribe.com>
32. <http://www.naturefootwear.com.au>, Nature has made shoes by using innovative pineapple textile, Pinatex.
33. Velarde A, Cazarer M, Dessertos cactus leather is the latest eco-friendly fabric, <http://www.greenmatters.com>, November 6, 2019.
34. New designer vegan leather handbags are made from mangoes, <http://www.livekindly.com>, March 7, 2020.
35. Vegan leather made from mushroom could mould the future of the sustainable fashion, The Conversation, <http://www.theconversation.com>
36. Kerelia G, Kerala startup makes water resistant leather alternative out of coconut water, 19th May 2020, <http://www.thebetterindia.com>
37. Solatorio N, Liao CC, Synthesis of cellulose by Acetobacter Xylinum: A comparison vegan leather to animal and imitation leather, University of Wyoming, Honors Programme, 2019.
38. García C, Prieto MA (2018) Bacterial cellulose as a potential bio leather substitute for the footwear industry. Microb Biotechnol 918373112:1-4.
39. <http://www.naturefootwear.com.au>, Nature has made shoes by using innovative pineapple textile, Pinatex.
40. <http://www.amexessentials.com>, Pineapple leather: The skin you are (Not) in- Amex essentials.
41. <http://www.materialdistrict.com>, Waterproof hemp shoes- Material District, Retrieved on 2nd July, 2019.
42. Nair AB, Joseph R, 9-Eco-friendly bio-composites using natural rubber (NR) matrices and natural fibre reinforcements in Chemistry, manufacture and application of natural rubber, Woodhead Publishing, 2014; 249-284
43. Lopattanon N, Panawarangkul A, Sahakaro K, Ellis B, Performance of pineapple leaf fibre and banana fibre composite: The effect of fibre surface treatments, Journal of Applied Polymer Science, 2006; 102: 1974-1984.
44. Sheesley HA, Artificial leather composition, US patent US 2146771A, 1935.
45. Wool R, Composites having leather like characteristics, US2013033771A1, 2013, United States.
46. Almal MS, Jute/cotton composites for use in the manufacture of footwear components and method of manufacture of such composites. W02002018691A2.
47. Meyer M, Dietrich S, Mondschein A, Comparison of technical performance of leather, artificial leather and trendy alternatives, Coatings, 2021; 11:226-234.
48. Samant, L., Goel, A., Mathew, J., Jose, S., Thomas, S (2023) Effect of surface treatment on flax fibre reinforced natural rubber green composite, Journal of Applied Polymer Science, 2023, DOI: 10.1002/app.53651

BTRA Facility :

DSC : Differential scanning calorimeter (DSC) is a method of thermal analysis that determines the temperature and heat flow associated with material transitions as a function of temperature or time.

Some of the important application of DSC are

- | | |
|---------------------|-----------------------------------|
| 1) Glass Transition | 4) Specific Heat |
| 2) Melting Point | 5) Curing Kinetics |
| 3) % Crystallinity | 6) Oxidative Induction Time (OIT) |

We have DSC 8000 with high pressure assembly in which we can go upto maximum 500psi. It is very useful for studying high pressure Oxidation Induction Time (HPOIT) of oils, Polyolefin Geosynthetics etc. under pressure.



Contact for more details :
 Email : info@btrainida.com
 Tel. : +91-22-6202 3636